

# Perfection :

## Finishes

### High Performance Polyurethane Gloss Finish



#### PRODUCT DESCRIPTION

Perfection : 2-part polyurethane is the ultimate performing, high gloss topside finish. It provides the longest-lasting, ultra-high gloss finish that has superb colour-retention, together with excellent chemical and abrasion resistance. It has been formulated specifically to enable skilled amateur users to achieve professional-quality results with ease. UV filters combined with the chemical cure of the polyurethane give the longest life possible.

\* Hardest, abrasion-resistant finish making it an excellent choice for use on high wear areas e.g. decks (with Intergrip additive).

\* Chemically resistant to diesel, petrol, oil, mild acids and alkalis

#### PRODUCT INFORMATION

<b>Colour</b>	YHA183-Platinum, YHA184-Med. White, YHA198-Mat'horn White, YHA216-Royal Blue, YHB000-Snow White, YHB663-Jade Mist Green, YHF991-Mauritius Blue, YHS070-Cream, YHS299-Rochelle Red, YHY999-Jet Black
<b>Finish</b>	High Gloss
<b>Specific Gravity</b>	1.17
<b>Volume Solids</b>	49%
<b>Mix Ratio</b>	2:1 by volume (as supplied)
<b>Converter/Curing Agent</b>	YGB001
<b>Typical Shelf Life</b>	2 yrs
<b>VOC (As Supplied)</b>	486 g/lit
<b>Unit Size</b>	750 ml

#### DRYING/OVERCOATING INFORMATION

	Drying							
	5°C (41°F)		15°C (59°F)		23°C (73°F)		35°C (95°F)	
Touch Dry	11 hrs		7 hrs		4 hrs		3 hrs	
Pot Life	5 hrs		3 hrs		2 hrs		1 hrs	

  

	Overcoating							
	Substrate Temperature							
	5°C (41°F)		15°C (59°F)		23°C (73°F)		35°C (95°F)	
Overcoated By	Min	Max	Min	Max	Min	Max	Min	Max
Perfection :	28 hrs	4 days	14 hrs	3 days	6 hrs	2 days	4 hrs	1 days

#### APPLICATION AND USE

<b>Preparation</b>	<p><b>PREVIOUSLY PAINTED SURFACES</b></p> <p><b>In Good Condition</b> Wash down with a suitable detergent, rinse with fresh water and allow to dry. Abrade with 280-320 grade (grit) paper.</p> <p><b>In Poor Condition</b> Remove all previous coatings and prime the substrate.</p> <p><b>PRIMING</b> All preparation for bare substrates is covered on the appropriate primer datasheet.</p> <p><b>BARE WOOD</b> Prime with Everdure or Interprotect.</p> <p><b>STEEL</b> Prime with Interprotect.</p> <p><b>ALUMINIUM</b> Pre-prime using Etch Primer. Prime with Interprotect.</p> <p><b>GRP</b> Wash down with a suitable detergent, rinse with fresh water and allow to dry. Abrade with 180-220 grade paper. No priming necessary.</p> <p><b>ALL SUBSTRATES</b> Use Perfection Undercoat.</p>
<b>Method</b>	<p>Sand the undercoat smooth with 320-400 grade (grit) wet or dry paper. Remove dust with a tack rag. Apply a full coat. Apply a further 1 or 2 full coats (depending on colour) to achieve full coverage.</p>
<b>Hints</b>	<p><b>Mixing</b> Stir contents of each part prior to mixing. Add Curing Agent to the Base, stir and leave for 20 minutes to allow bubbles to disperse.</p> <p><b>Thinner</b> YTA006 International Retarder Thinners #9.</p> <p><b>Cleaner</b> YTA006 International Retarder Thinners #9.</p> <p><b>Ventilation and Humidity Control</b> Apply in dry, well ventilated conditions. Avoid excessively humid conditions, over 80% relative humidity.</p> <p><b>Other</b> Best applied at 15°C. For lighter colors, mix the first coat of finish 50:50 with the undercoat to improve the depth of color and opacity. Both products should be mixed with respective curing agents first. For best results when applying by roller, smooth off with a pad or brush. If using as a deck paint, mix in non-slip additive. Full hardness is achieved after 7-10 days at 15°C/59°F.</p>

Please refer to your local representative or visit <http://www.yachtpaint.com> for further information.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies. © AkzoNobel 2014.

# Perfection :

## Finishes

### High Performance Polyurethane Gloss Finish

<b>Some Important Points</b>	Do not use unless mixed thoroughly with the curing agent at specified ratio. Avoid painting in direct sunlight. Avoid applying late in the evening as condensation can cause a loss of gloss during overnight cure. Allow to dry in a well ventilated environment. Product temperature should be minimum 15°C/59°F and maximum 35°C/95°F. Ambient temperature should be minimum 5°C/41°F and maximum 30°C/86°F. Substrate temperature should be minimum 5°C/41°F and maximum 30°C/86°F.
<b>Compatibility/Substrates</b>	Do not use Perfection : on flexible constructions. Will crack on carvel and clinker/lapstrake hulls. Perfection : should not be used over any one-pack products. Not suitable for permanently immersed surfaces.
<b>Number of Coats</b>	2-3
<b>Coverage</b>	(Theoretical) - 13.3 m <sup>2</sup> /lt (Practical) - 12 m <sup>2</sup> /lt
<b>Recommended DFT per coat</b>	37 microns dry
<b>Recommended WFT per coat</b>	76 microns wet
<b>Application Methods</b>	Brush, Roller, DO NOT SPRAY

#### TRANSPORTATION, STORAGE AND SAFETY INFORMATION

<b>Storage</b>	<b>GENERAL INFORMATION:</b> Exposure to air and extremes of temperature should be avoided. For the full shelf life of this product to be realised ensure that between use the container is firmly closed and the temperature is between 5°C/41°F and 35°C/95°F. Keep out of direct sunlight. <b>TRANSPORTATION:</b> Perfection : should be kept in securely closed containers during transport and storage.
<b>Safety</b>	<b>GENERAL:</b> Contains isocyanates which may be harmful to the respiratory tract. Read the label safety section for Health and Safety Information, also available from our Technical Help Line. <b>DISPOSAL:</b> Do not discard tins or pour paint into water courses, use the facilities provided. It is best to allow paints to harden before disposal. Remainders of Perfection : cannot be disposed of through the municipal waste route or dumped without permit. Disposal of remainders must be arranged for in consultation with the authorities.
<b>IMPORTANT NOTES</b>	<i>The information given in this sheet is not intended to be exhaustive. Any person using the product without first making further written enquiries as to the suitability of the product for the intended purpose does so at their own risk and we can accept no responsibility for the performance of the product or for any loss or damage (other than death or personal injury resulting from negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.</i>